

WATHEROO MINERALS PTY LTD

ABN 24 052 236 325

Trading As

BENTONITE WA

SCOTT'S WATHEROO DOLOMITE

PO Box 44, KARRINYUP WA 6018

Email: info@bentoniteproductswa.com.au

Phone: (08) 9205 1815

Facsimile: (08) 9205 1926

Anode backfill and earthing product: B1

Mix of calcium bentonite and gypsum. Used as backfill and for applications where a low electrical resistivity is required.

Composition:

Calcium bentonite	50 % by mass
Gypsum (calcium sulphate)	50 % by mass

Technical specifications.

As for Type B1 backfill, AS2239

Resistivity as measured by AS1289.4.4.1 Calcium bentonite, low swelling preparation	2 ohm.m
Maximum dry density (MDD)	2.01 T/m ³
Density of bagged product	~1.2
Moisture content	8-12%
pH 5 % suspension	7.5-8.0
Particle size	100 % less than 1 mm
Appearance	Light grey powder
Available as:	25 kg bag 1T bulka